



GEOTURF® N1600 NONWOVEN GEOTEXTILE FABRIC

A nonwoven geotextile fabric supplied by CSI Geoturf, Inc., is manufactured from polypropylene staple fiber. The fibers are randomly oriented and form a cohesive / stabilized needle punched fabric for use in many applications, such as separation, drainage, filtration, etc. This fabric has been UV stabilized and is resistant to commonly encountered chemicals, mildew and insects found in soil.

March 2020

Property	Test Method	Minimum Average Roll Value*	
		ENGLISH	
Grab Tensile Strength	ASTM D-4632	380	lbs.
Grab Elongation	ASTM D-4632	50	%
Trapezoid Tear	ASTM D-4533	145	lbs.
Puncture (CBR)	ASTM D-6241	1025	lbs.
Permittivity	ASTM D-4491	.6	sec ⁻¹
A.O.S.	ASTM D-4751	100	U.S. Sieve
UV Stability (500 hrs)	ASTM D-4355	70	%
Water Flow Rate	ASTM D-4491	50	gpm/ft ²
Notes:	-Mullen Burst ASTM D3786 removed. Not recognized by ASTM D35 on Geosynthetics. -Puncture ASTM D4833 is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D6241. -Properties subject to change without notice.		

This information is to the best of our knowledge and belief accurate as of the date compiled. However no guarantee is made as to its accuracy reliability or completeness. It is the user's responsibility to satisfy his/her self as to the suitability and completeness of such information for his or her own particular use. We do not accept liability for any loss or damage that may occur from the use of this information nor do we offer any warranty against infringement.