



GEOTURF® W315 WOVEN GEOTEXTILE FABRIC

A woven geotextile fabric, produced from high-tenacity polypropylene slit-film. This high-modulus fabric is ideally suited for separation / stabilization applications. This fabric has been UV stabilized and packaged in conformance with ASTM D4873.

May 2019

Property	Test Method	Minimum Average Roll Value* ENGLISH	
Grab Tensile Strength	ASTM D-4632	315	lbs.
Grab Elongation	ASTM D-4632	15	%
Trapezoid Tear	ASTM D-4533	113	lbs.
Puncture (CBR)	ASTM D-6241	900	lbs.
Permittivity	ASTM D-4491	.050	sec ⁻¹
A.O.S.	ASTM D-4751	40	U.S. Sieve
UV Stability (500 hrs)	ASTM D-4355	70	%
Water Flow Rate	ASTM D-4491	4.0	gpm/ft ²
Notes:	-Mullen Burst ASTM D3786 removed. Not recognized by ASTM D35 on Geosynthetics. -Puncture ASTM D4833 is not recognized by AASHTO M288 and has been replaced with CBR Puncture ASTM D6241. -Properties subject to change without notice.		

This information is to the best of our knowledge and belief accurate as of the date compiled. However no guarantee is made as to its accuracy reliability or completeness. It is the user's responsibility to satisfy his/her self as to the suitability and completeness of such information for his or her own particular use. We do not accept liability for any loss or damage that may occur from the use of this information nor do we offer any warranty against infringement.